




Heat Transfer Vinyl Cutting, Peeling and Pressing Guide

Cutting

Vivid Flex Heat Transfer Vinyl can be used on almost every vinyl cutter, just make sure you do a **test cut first** to get the correct settings for your cutter.

Here are our recommended settings for the most commonly used cutters:



Patterned HTV Vinyl:

Blade: 4

Thickness/force: 14

All Other HTV Vinyl:

Blade: 6

Thickness/force: 16



All Vinyl:

Card stock settings

(test cut first)



All Vinyl:

Blade: 5

Cut Pressure: 8

(test cut first)

Pressing Times

Heat Press

Time: 8 - 10 sec

Temp: 150c

Clothes Iron

Settings: Cotton/Wool

Time: 30 sec

Peeling - **WARM PEEL**

Vivid Flex Heat Transfer Vinyl is a **WARM PEEL** unless otherwise stated.

To ensure proper transferring of the vinyl to the garment, after heat is applied, allow 10-20 seconds before peeling the backing layer. If peeled too soon the vinyl will appear to lift as this is a warm and not hot peel. If this occurs wait for 3 - 5 seconds and then peel from the other corner and if need be re-press with good quality baking paper.

